



110 Emerson Place,
Brooklyn, NY 11205
t: 718.399.3333
e: sales@sfsupplies.com
w: sfsupplies.com

DURA-FOAM

PVC Foam Board

TECHNICAL VALUES

	PROPERTY	UNIT	TEST METHOD	VALUE
A]	PHYSICAL			
	DENSITY	g/cc	DIN 53479	0.66 - 0.75
	HARDNESS	SHORE'D'	DIN 53505	≥ 42
	1 - 7 mm			≥ 47
	8 - 12 mm			≥ 55
	12.7 - 25 mm			≥ 55
	WATER ABSORPTION (24HR/23 C)	%	DIN 53495	<1.0
B]	MECHANICAL			
	TENSILE STRENGTH	MPa	DIN 53455	>15.0
	ELONGATION AT BREAK		DIN 53455	
	FOR WHITE COLOR	%		≥ 15
	FOR OTHER COLOR	%		≥ 9
	MODULUS OF ELASTICITY	MPa	DIN 53457	900 - 1500
	IZOD IMPACT STRENGTH (3 - 12 mm)	KJ/m ²	ASTM D 256	≥ 9.0
C]	THERMAL			
	VICAT SOFTENING TEMPERATURE (A/50)	°C	DIN 53460	≥ 73
D]	FLAMMABILITY			
	LIMITING OXYGEN INDEX	%	ASTM D 2863	>40
	FREE BEHAVIOR		BS 476:PART7-1987	CLASS IY
			UL 94	94VO
			NFP 92-501	M1
E]	DIMENSIONAL TOLERANCES			
	THICKNESS	mm	± [0.1mm + 0.05 x s]	
	TO CALCULATE	THICKNESS IN	mm x 0.05 + 0.1	
	LENGTH	mm	-0, +10	
	WIDTH	mm	-0, +5	
	DEVIATION BETWEEN DIAGONALS	mm	≤ 6	
	WARPAGE (ON A FULL SHEET)	mm	≤ 10	
F]	VISUAL			
	SURFACE (VIEWED FROM A DISTANCE OF 1.5 M)	SMOOTH MATT		

AVAILABILITY

1. COLORS & CODES

(COLOR SHEETS ARE NORMALLY AVAILABLE IN 3mm, 4mm, 5mm AND 6mm THICKNESS ONLY)

SUPER WHITE	J1018	RED	J4021	GREEN	J6021
YELLOW	J2021	RUBY RED	J4151	BEIGE	J2211
SKY BLUE	J7021	ORANGE	J3021	GOLD	J5021
ROYAL BLUE	J7051	GREY	J8021	SILVER GREY	J8033
BLACK	J9021				

2. THICKNESS : 1 to 10mm up to 1220mm width, 3 to 10mm in higher width.
3. WIDTHS (mm) : 1000, 1220, 1560, 2050.
4. LENGTHS (mm) : 2000, 2440, 3000, 3050, 5490, 6100.
SPECIAL LENGTHS & WIDTHS AS PER CUSTOMER'S REQUEST

ALL INFORMATION GIVEN FOR PROPERTIES ARE BASED ON A TYPICAL SAMPLE, IS ACCURATE TO THE BEST OF OUR KNOWLEDGE, AND IS PROVIDED WITHOUT LIABILITY OR COMMITMENT WHATSOEVER. IN AS MUCH AS JAIN IRRIGATION SYSTEMS LIMITED HAS NO CONTROL OVER THE USE TO WHICH OTHERS PUT ITS MATERIAL, IT DOES NOT GUARANTEE THAT THE SAME RESULTS AS THOSE DESCRIBED HERE, WILL BE OBTAINED. EACH USER OF THE MATERIAL SHOULD MAKE THEIR OWN TEST IN THEIR OWN LOCAL CONDITIONS TO CONFIRM THE SUITABILITY OF OUR PRODUCT FOR PARTICULAR USE. TECHNICAL SPECIFICATIONS ARE SUBJECT TO CHANGE.

ISSUE DATE 01.01.1994, REVISION NO. 04, DATE 01.06.2003

METRIC UNITS (GENERAL)